


20 MIL REINFORCED



Griffolyn® 20 Mil Reinforced is a multiply laminate combining U.V. stabilized film with a high strength cord grid. It is specifically engineered to provide high strength and durability in a lightweight material.

PHYSICAL PROPERTIES AND TYPICAL VALUES	PROPERTY	ASTM TEST METHOD	U.S. VALUE	METRIC VALUE
	Weight	D-751	93 LB/1000 FT ²	45 KG/100 M ²
	Thickness	D-2103	20 MIL	50 MM
	3" Load @ Yield	D-882	150 LBF	667 N
	3" Elongation @ Break	D-882	400 %	400 %
	Tongue Tear	D-2261	36 LBF	160 N
	Trapezoidal Tear	D-4533	55 LBF	245 N
	Permeance	E-96	0.019 Grain/Hr•Ft ² •In.Hg	1.06 NG/(PA•S•M ²)

FEATURES

AVAILABLE COLORS:

White

SIZES:

Standard rolls from 4' x 100' to 40' x 100' in increments of 4' widths. Standard length and width tolerances are $\pm 1\%$ (minimum 2")

Custom sizes up to 100' x 200' and custom fabrication are available to meet your exact specifications.

USABLE TEMPERATURE RANGE:

Minimum: -40°F -40°C

Maximum: 170°F 77°C

The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, expressed or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

©2010 REEF INDUSTRIES, INC. Griffolyn is a registered trademark of Reef Industries, Inc. 02-10

TOLLFREE 1.800.231.6074

9209 Alameda Genoa Rd. • Houston, Texas 77075

P: 713.507.4251 • F: 713.507.4295

Email: ri@reefindustries.com

REEF INDUSTRIES, INC.

The Manufacturing Leader of Specialized Industrial Plastic Films Since 1957.

20 MIL REINFORCED

GRIFFOLYN®

PRODUCT INFORMATION • SPECIFICATION GUIDE

