

L30 BLACK

Permalon®



Reef L30 Black is a high strength and durable liner material engineered to work in many environments. It is specifically engineered to provide high strength and durability in a lightweight material. Reef L30 is a LLDPE polyethylene product.

PHYSICAL PROPERTIES AND TYPICAL VALUES	PROPERTY	ASTM TEST METHOD	U.S. VALUE	METRIC VALUE
	Weight	D-2103	148 LB/1000 FT ²	72.2 KG/100M ²
	Thickness	D-2103	30 MIL	0.76 MM
	Density	D-1505	0.939 G/CC	0.939 G/CC
	3" Load @ Break	D-882	110 LBF	489.3 N
			3650 PSI	25.2 MPA
	3" Elongation @ Break	D-882	750 %	750 %
	Tongue Tear	D-1004	55 LBF	245 N
	Trapezoidal Tear	D-4533	85 LBF	378 N
	Permeance	E-96	.013 Grain/Hr•Ft ² •in.Hg	0.72 NG/(PA•S•M ²)
	Dart Impact Strength	D-1709	> 5.0 LBS	> 2200 g
	Puncture Strength	D-4833	65 LBF	289 N
Carbon Black Content	D-1603	2 %	2 %	
Oxidative Induction Time	D-3895	100 Minutes	100 Minutes	

REEF INDUSTRIES, INC.

The Manufacturing Leader of Specialized Industrial Plastic Films Since 1957.

L30 BLACK

PERMALON®

PRODUCT INFORMATION • SPECIFICATION GUIDE

The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, expressed or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

TOLLFREE 1.800.231.6074

9209 Alameda Genoa Rd. • Houston, Texas 77075

P: 713.507.4251 • F: 713.507.4295

Email: ri@reefindustries.com

