



Griffolyn® Type-105 is a 7-ply laminate combining four layers of high density polyethylene and three high-strength cord grids. It is specifically engineered to provide high strength and durability in a lightweight material.

PHYSICAL PROPERTIES AND TYPICAL VALUES			
PROPERTY	ASTM TEST METHOD	U.S. VALUE	METRIC VALUE
Weight	D-3776	90 LB/1000 FT ²	44 KG/100 M ²
3" Tensile Strength	D-882	275 LBF	1220 N
Puncture Strength	D-4833	72 LBF	320 N
PPT Resistance	D-2582	50 LBF	222 N
Dart Impact Strength	D-1709	5.0 LBS	2300 g
Cold Impact Strength	D-1790	-40°F	-40°C
Permeance	E-96	0.021 Grain/Hr•Ft ² •in.Hg	1.207 NG/(PA•S•M ²)

FEATURES

- Multiple layers and cord reinforcement resist punctures and tears.
- UV stabilization protects the material from degradation during extended exposure to sunlight.
- Cold-crack resistance eliminates failures in extremely cold temperatures.
- Chemically resistant to withstand exposure without significant deterioration.
- Low permeability greatly inhibits moisture transmission.
- Flexibility and light weight allow for easy handling and quick installation.
- Custom fabrication is available to meet your exact specifications.
- High durability allows for significant savings through reuse and fewer replacements.
- Class A, ASTM E-1745-97 Standard Specification for Water Vapor Retarders Used in Contact With Soil or Granular Fill Under Concrete Slabs.

The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, expressed or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

TOLLFREE 1.800.231.6074

9209 Alameda Genoa Rd. • Houston, Texas 77075
 P: 713.507.4251 • F: 713.507.4295
 Email: ri@reefindustries.com



SUGGESTED APPLICATIONS

- Pallet, cable reel and drum covers for outside storage.
- Floor covers, dust partitions and cleanroom enclosures.
- Temporary walls, plant dividers, building enclosures and containment tents.
- Architectural vapor retarder for underslab, walls & ceilings and in roofing systems.
- Shipping container covers and liners.
- Soil covers to control leachate for stockpiles and landfills.
- Erosion control and slope protection covers.
- Agricultural storage systems, hay covers and windbreaks.
- Athletic field and equipment covers.

ORDERING INFORMATION

AVAILABLE COLORS:

Black

SIZES:

Standard rolls from 4' x 100' to 40' x 100' in increments of 4' widths are available for immediate shipment. Standard length and width tolerances are $\pm 1\%$ (minimum 2")

Custom sizes up to 100' x 200' and custom fabrication are available to meet your exact specifications.

USABLE TEMPERATURE RANGE:

Minimum: -45°F -42°C

Maximum: 170°F 77°C

OUTDOOR EXPOSURE

Under normal continuous exposure the average life expectancy ranges from 30 to 48 months.

The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, expressed or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

©2006 REEF INDUSTRIES, INC. Griffolyn is a registered trademark of Reef Industries, Inc. 10-07

TOLLFREE 1.800.231.6074

9209 Almeda Genoa Rd. • Houston, Texas 77075

P: 713.507.4251 • F: 713.507.4295

Email: ri@reefindustries.com

