


GRIFFOLYN® TX 1200 ANTIMICROBIAL



Griffolyn® TX-1200 Antimicrobial is a 3-ply, nonmigratory, blended laminate combining two layers of linear low density polyethylene and a high-strength cord grid. It is specifically engineered to provide high strength and durability in a lightweight material.

| PHYSICAL PROPERTIES AND TYPICAL VALUES | PROPERTY | ASTM TEST METHOD | U.S. VALUE | METRIC VALUE |
|--|-----------------------|------------------|----------------------------|--------------------------|
| | Weight | D-751 | 34 LB/1000 FT ² | 17 KG/100 M ² |
| | 3" Load @ Yield | D-882 | 92 LBF | 409 N |
| | 3" Load @ Break | D-882 | 55 LBF | 245 N |
| | | | 2350 PSI | 16 MPA |
| | 3" Elongation @ Break | D-882 | 300 % | 300 % |
| | Tongue Tear | D-2261 | 15 LBF | 67 N |
| | Trapezoidal Tear | D-4533 | 33 LBF | 147 N |
| | PPT Resistance | D-2582 | 32 LBF | 142 N |
| | Dart Impact Strength | D-1709 | 2 LBS | 1 KG |
| Cold Impact Strength | D-1790 | -40°F | -40°C | |
| Puncture Strength | D-4833 | 25 LBS | 111 N | |

FEATURES

- Non-migratory.
- Wash resistant.
- Very stable in a wide range of environments across a broad temperature range.
- Non-toxic and environmentally safe.
- Durable and tear resistant.

ORDERING INFORMATION

AVAILABLE COLORS:

White

SIZES:

Standard rolls from 4' x 100' to 40' x 100' in increments of 4' widths are available for immediate shipment. Standard length and width tolerances are ± 1% (minimum 2")

USABLE TEMPERATURE RANGE:

Minimum: -40°F -40°C

Maximum: 170°F 77°C

The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, expressed or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

©2011 REEF INDUSTRIES, INC. Griffolyn is a registered trademark of Reef Industries, Inc. 02-11

TOLLFREE 1.800.231.6074

9209 Alameda Genoa Rd. • Houston, Texas 77075

P: 713.507.4251 • F: 713.507.4295

Email: ri@reefindustries.com

REEF INDUSTRIES, INC.

The Manufacturing Leader of Specialized Industrial Plastic Films Since 1957.

TX 1200 ANTIMICROBIAL

GRIFFOLYN®

PRODUCT INFORMATION • SPECIFICATION GUIDE

