



Griffolyn® TX-1200 FR is a 3-ply laminate combining two layers of fire retardant, linear, low density polyethylene and a high-strength cord grid. It is specifically engineered to provide high strength and durability in a lightweight material.

**PHYSICAL PROPERTIES AND TYPICAL VALUES**

PROPERTY	ASTM TEST METHOD	U.S. VALUE	METRIC VALUE
Weight	D-3776	45 LB/1000 FT <sup>2</sup>	22 KG/100 M <sup>2</sup>
3" Tensile Strength	D-882	135 LBF	600 N
Puncture Strength	D-4833	43 LBF	191 N
PPT Resistance	D-2582	35 LBF	156 N
Dart Impact Strength	D-1709	2.4 LBS	1.09 kg
Cold Impact Strength	D-1790	-10°F	-23.4°C
Permeance	E-96	0.036 Grain/Hr•Ft <sup>2</sup> •in.Hg	2.06 NG/(PA•S•M <sup>2</sup> )
Fire Retardancy	E-84	5 flame spread, 50 smoke developed	
	NFPA 701	Pass	

Conforms to the following safety codes:

- Passes NFPA 701 Test 2 (Large Scale) – “Standard Methods of Fire Tests for Flame Propagation of Textiles and Films”.
- Class I, Class A flame spread rating per UBC-42 and ASTM E-84.

**FEATURES**

- Multiple layers and cord reinforcement resist punctures and tears.
- Cold-crack resistance eliminates failures in cold temperatures.
- Low permeability greatly inhibits moisture transmission.
- Flexibility and light weight allow for easy handling and quick installation.
- Custom fabrication is available to meet your exact specifications.
- Long life expectancy allows for significant cost savings through reuse and fewer replacements.

**SUGGESTED APPLICATIONS**

- Temporary walls, plant dividers, building enclosures and containment tents.
- Floor covers, dust partitions and cleanroom enclosures.
- Architectural vapor retarder in walls & ceilings and in roofing systems.
- Pallet, cask and drum covers for outside storage.
- Shipping container covers and liners.

The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, expressed or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

**TOLLFREE 1.800.231.6074**

9209 Alameda Genoa Rd. • Houston, Texas 77075  
 P: 713.507.4251 • F: 713.507.4295  
 Email: [ri@reefindustries.com](mailto:ri@reefindustries.com)



## ORDERING INFORMATION

### AVAILABLE COLORS:

Natural and Yellow

### SIZES:

Standard rolls from 4' x 100' to 40' x 100' in increments of 4' widths are available for immediate shipment. Standard length and width tolerances are  $\pm 1\%$  (minimum 2")

Custom sizes up to 100' x 200' and custom fabrication are available to meet your exact specifications.

### USABLE TEMPERATURE RANGE:

Minimum: -15°F -27°C

Maximum: 170°F 77°C

## OUTDOOR EXPOSURE

Under normal continuous exposure the average life expectancy ranges from 10 to 12 months, depending on color.

The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, expressed or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

©2009 REEF INDUSTRIES, INC. Griffolyn is a registered trademark of Reef Industries, Inc. 05-09

**TOLLFREE 1.800.231.6074**

9209 Alameda Genoa Rd. • Houston, Texas 77075

P: 713.507.4251 • F: 713.507.4295

Email: [ri@reefindustries.com](mailto:ri@reefindustries.com)

